



ZÜMRÜT İNTERNATİONAL KİMYA

Natural Asphalt Gilsonite (5-10%)

Color in Mass	Black
Color in streak or powder	Black
Softening point	160-220 C
Moisture Content	<3
Specific gravity@77°F	1.02-1.2
Hardness (mohr s scale)	2
Penetration	0
Flash point,°C, C.O.C	>290
Trace elements	<1
Solubility in T.C.E., Wt%	70-85
Solubility in CS₂,Wt%	70-90
Ash	5-10
Fixed Carbone	25-35



No 207, 30th floor Kule2
Sinpaş Altin Oran Çankaya, Ankara-Turkey



www.zumrut-int.com



+90 555 160 57 39
+90 312 544 45 81



Info@zumrut-int.com