



ZÜMRÜT INTERNATIONAL KİMYA SAN. VE TİC.LTD

Styrene Butadiene Rubber (SBR)

Molar mass Mn, g/mol	200000
Molar mass Mw, g/mol	420000
Mw / Mn	2.1
Styrene content , %	18
Cis- 1,4- content, %	35
Trans- 1,4 -content, %	54
1,2- content ,%	11
Glass Transition temperature T _g , C	-69.7



Karşıyaka mahallesi,749 sokak ,No 30 ,
Gölbaşı/Ankara/Türkiye



www.zumrut-int.com



+90 555 160 57 39
+90 312 544 45 81



Info@zumrut-int.com