



ZÜMRÜT INTERNATIONAL KİMYA SAN. VE TİC.LTD

Technical Data Sheet of Blown Asphalt 75/25

Bitumen 75/25	Test method	Unit	Specification
Specific gravity @25/25 C	ASTM D70	(Kg/m3)	1.05 approx.
Penetration @ 25°C	ASTM D5	mm/10	20/30
Softening point °C	ASTM D36	°C	70/80
Loss on heating(wt) %	ASTM D6	Wt. %	0.2 max
Flashpoint c	ASTM D92	°C	250 min
Solubility is CS2(wt) %	ASTM D4	Wt. %	99.5 max
Spot test	A.A.S.H.T.O 102	—	Negative



Karşıyaka mahallesi,749 sokak ,No 30 ,
Gölbaşı/Ankara/Türkiye



www.zumrut-int.com



+90 555 160 57 39
+90 312 544 45 81



Info@zumrut-int.com