



ZÜMRÜT INTERNATIONAL KİMYA SAN. VE TİC.LTD

Technical Data Sheet of Oxidized Bitumen 95/25

Bitumen <u>95/25</u>	Test method	Unit	Specification
Specific gravity @25/25 C	ASTM D70	(Kg/m3)	1.05 approx.
Penetration @ 25°C	ASTM D5	mm/10	20/30
Softening point °c	ASTM D36	°C	90/100
Loss on heating(wt) %	ASTM D6	Wt. %	0.2 max
Flashpoint °c	ASTM D92	°C	250 min
Solubility is CS2(wt) %	ASTM D4	Wt. %	99.5 max
Ductility@25 C	ASTM D113	—	1.5 min



Karşıyaka mahallesi,749 sokak ,No 30 ,
Gölbaşı/Ankara/Türkiye



www.zumrut-int.com



+90 555 160 57 39
+90 312 544 45 81



Info@zumrut-int.com