



ZÜMRÜT İNTERNATİONAL KİMYA

Technical Data Sheet of Blown Asphalt 115/15

Bitumen 115/15	Test method	Unit	Specification
Specific gravity @25/25 C	ASTM D70	(Kg/m3)	1.05 approx.
Penetration @ 25°C	ASTM D5	mm/10	20-Oct
Softening point °c	ASTM D36	°C	110/120
Ductility @25 °c	ASTM D113	Cm	1.5min
Loss on heating(wt) %	ASTM D6	Wt. %	0.2 max
Flashpoint c	ASTM D92	°C	250 min
Solubility is CS2(wt) %	ASTM D4	Wt. %	99.5 max
Spot test	A.A.S.H.O.T102	—	Negative



No 207, 30th floor Kule2
Sinpaş Altın Oran Çankaya, Ankara-Turkey



www.zumrut-int.com



+90 555 160 57 39
+90 312 544 45 81



Info@zumrut-int.com