



ZÜMRÜT INTERNATIONAL KİMYA SAN. VE TİC.LTD

Technical Data Sheet of Blown Asphalt 75/35

Bitumen 75/35	Test method	Unit	Specification
Specific gravity @25/25 C	ASTM D70	(Kg/m3)	1.05 approx.
Penetration @ 25°C	ASTM D5	mm/10	30/40
Softening point °C	ASTM D36	°C	70/80
Loss on heating(wt) %	ASTM D6	Wt. %	0.2 max
Flashpoint c	ASTM D92	°C	250 min
Solubility is CS2(wt) %	ASTM D4	Wt. %	99.5 max
Spot test	A.A.S.H.T.O 102	—	Negative

Advantages

- **Enhanced Elasticity and Durability:** Ideal for applications exposed to stress and environmental conditions.
- **Good Water Resistance:** Provides effective protection in waterproofing applications.
- **Flexibility:** Suitable for use in climates with temperature variations.

Packaging

- **Drums:** Typically supplied in 180-kg or 200-kg drums, depending on client specifications.
- **Bulk:** Available in bulk for industrial applications.



Karşıyaka mahallesi,749 sokak ,No 30 ,
Gölbaşı/Ankara/Türkiye



www.zumrut-int.com



+90 555 160 57 39
+90 312 544 45 81



Info@zumrut-int.com