



ZÜMRÜT INTERNATIONAL KİMYA SAN. VE TİC.LTD

Specification of cutback bitumen SC-3000

property	specification limit	Test method	
	Min	Max	
Kinematic viscosity at 60°C [140°F], mm ² /s	3000	6000	ASTM D2170
Flashpoint(Cleveland open cup), °C [°F]	70	—	ASTM D92
distillate test			
Total distillate to 360°C [680°F], volume %	—	8	ASTM D402
Solubility, %	95	—	ASTM D2024
Kinematic viscosity on distillation residue at 60°C [140°F], mm ² /s	2000	35000	ASTM D2170
Asphalt residue:			
Residue of 100 penetration, %	75	—	ASTM D243
Ductility of 100 penetration residue at 25°C [77°F], cm	50	—	ASTM D113
Water, %	—	0.5	ASTM D95



Karşıyaka mahallesi,749 sokak ,No 30 ,
Gölbaşı/Ankara/Türkiye



www.zumrut-int.com



+90 555 160 57 39
+90 312 544 45 81



Info@zumrut-int.com