

ZÜMRÜT INTERNATIONAL KİMYA SAN. VE TİC.LTD

Bitumen Penetration Grade 50/70 Specifications

Bitumen 50/70	Test method	Unit	Specification
Penetration - 25°C, 100g, 5s	EN 1426	mm	50-70
Softening Point (Ring & Ball)	EN 1427	°C	46/54
Kinematic Viscosity @ 135°C	EN 12595	mm²/s	295 Min
Penetration Index	EN 12591	-	-0.8
Solubility in Xylene	EN 12592	%	99 Min
Flashpoint (Cleveland Open)	EN 22592	°C	230 Min
Recistance to Hardening at 163 °C	3/4		
Change in mass (m/m)	EN12607-1	%	0.5 Max
Retained Penetration 25°C, 100g, 5s (% of original)	EN 1426	%	50 Min
Increase in softening point	EN 1427	°C	11 Max

Special Applications

- 1. Bridge Decks and Flyovers: Employed in the construction of bridge decks and flyovers, where materials need to accommodate structural movements and heavy loads.
- 2. Sports Courts and Playgrounds: Used in the construction of sports courts and playgrounds, providing a smooth and resilient playing surface.
- 3. Cycle Paths and Footpaths: Suitable for paving cycle paths and footpaths, ensuring a smooth and durable surface for pedestrians and cyclists.



+90 555 160 57 39 +90 312 544 45 81



Info@zumrut-int.com