



ZÜMRÜT INTERNATIONAL KİMYA SAN. VE TİC.LTD

Bitumen Penetration grade 20/30 Specifications

Bitumen 20/30	Test method	Unit	Specification
Penetration @ 25°C	EN 1426	mm/10	20/30
Softening point °C	EN 1427	°C	53/65
Kinematic Viscosity @ 135°C	EN 12595	mm ² /s	530 min
Flashpoint °C	EN 22592	°C	240 min
Solubility is CS2(wt) %	EN 12592	wt %	99 min



Karşıyaka mahallesi,749 sokak ,No 30 ,
Gölbaşı/Ankara/Türkiye



www.zumrut-int.com



+90 555 160 57 39
+90 312 544 45 81



Info@zumrut-int.com