

## **Cationic Bitumen emulsion CSS-1h Specification**

PropertyProperty	Min	Max	Test Method
Test on Emulsions			
Viscosity, Saybolt Furol at 25 °C, SFS	20	100	ASTM D244
Storage stability test, 24-h, %	_	1	ASTM D6930
Particle charge test	positive	ASTM D244	
Sieve test, %	- ,	0.1	ASTM D6933
Cement mixing test, %		2	ASTM D6935
Distillation:			
Residue, %	57	-	ASTM D244
Tests on residue from distillation test:			
Penetration, 25°C (77°F), 100 g, 5 s	40	90	ASTM D5
Ductility, 25°C (77°F), 5 cm/min, cm	40	-	ASTM D113
Solubility in trichloroethylene, %	97.5	-	ASTM D2042



+90 555 160 57 39 +90 312 544 45 81



Karşıyaka mahallesi,749 sokak ,No 30 , Gölbaşı/Ankara/Türkiye

