



ZÜMRÜT INTERNATIONAL KİMYA SAN. VE TİC.LTD

Specification of Anionic Bitumen Emulsion MS-2

PROPERTY	MIN	MAX	TEST METHOD
Viscosity, Saybolt Furol at 25 °C, SFS	20	100	ASTM D244
Storage stability, 24h (%)	—	1	ASTM D6930
Particle charge test	Minus	Minus	ASTM D244
Sieve (%)	—	0.1	ASTM D6933
Residue by distillation (%)	65		ASTM D244
Residue penetration, 25 °C	100	200	ASTM D5
Solubility in trichloroethylene %	97.5	—	ASTM D2042
Residue ductility, 25 °C, 5cm/min (cm)	40	—	ASTM D113



Karşıyaka mahallesi, 749 sokak, No 30,
Gölbaşı/Ankara/Türkiye



www.zumrut-int.com



+90 555 160 57 39
+90 312 544 45 81



Info@zumrut-int.com