



ZÜMRÜT INTERNATIONAL KİMYA SAN. VE TİC.LTD

Specification of Bitumen Emulsion K1-40

No	Property	Test Method	Min	Max
1	Saybolt fural viscosity @ 25°C sec	ASTM D224	—	25
2	Storage Stability (24 hours) %	ASTM D224	—	1
3	Sieve Test (%)	ASTM D224	—	0.1
4	Particle Charge Test	ASTM D224	Positive	—
5	Solubility in Trichloroethylene (% Mass)	ASTM D2042	97.5	—
6	Residue from distillation	ASTM D224	37	—
7	Penetration @ 25°C, 100g, 5sec	ASTM D5	60	200



Karşıyaka mahallesi, 749 sokak, No 30,
Gölbaşı/Ankara/Türkiye



www.zumrut-int.com



+90 555 160 57 39
+90 312 544 45 81



Info@zumrut-int.com