



ZÜMRÜT INTERNATIONAL KİMYA SAN. VE TİC.LTD

T.D.S of Cationic Bitumen Emulsion K3

No	Property	Result
1	Particle charge	Pos.
2	Residue on 710 um KS sieve %(m/m), maximum	0.05
3	Residue on 150 um KS sieve (g per 100 mL), maximum	0.15
4	Binder content %(m/m), minimum	57
5	Viscosity (degrees Engler (°E) at 20°C	10 max
6	Viscosity redwood No. II (s at 85°C)	—
7	Storage stability (long period test) % water content difference, maximum	2



Karşıyaka mahallesi, 749 sokak, No 30,
Gölbaşı/Ankara/Türkiye



www.zumrut-int.com



+90 555 160 57 39
+90 312 544 45 81



Info@zumrut-int.com