



ZÜMRÜT INTERNATIONAL KİMYA SAN. VE TİC.LTD

## Technical Data Sheet of Tiles and ceramics

Parameter	Specification
Swelling index (2gr)	18-20
Gelling index (24 hours)	14
Percentage of Montmorillonite (MN 616)	50-54
Water Absorption (24h)	500-550
Percentage of Moisture (%)	12-Oct
Residue of diameter greater than 200mesh (%)	Maximum 6



Karşıyaka mahallesi,749 sokak ,No 30 ,  
Gölbaşı/Ankara/Türkiye



[www.zumrut-int.com](http://www.zumrut-int.com)



+90 555 160 57 39  
+90 312 544 45 81



[Info@zumrut-int.com](mailto:Info@zumrut-int.com)